

BPIX Module Testing Status - week 49

5th January 2007

Production Status: 308 modules produced

- 213/40 graded as A/B → 82%
- 55 graded as C → 18%

Testing Status of week 49:


- 11 modules fully tested and therm. cycled

Grade	A	B	C
T = -10° C, BTC*	10	0	1
T = -10° C, ATC	9	1	1
T = $+17^{\circ}$ C, ATC	9	1	1
Final Grade	8	2	1

- 7 partially tested / testing failed
- no retests


*without IV-criteria

Production summary




Module Failures Overview


Grade B




Grade C



Grade B




Grade C Failures




Defective pixel $T = 17^{\circ}\text{C}$ (ATC)

Overlay of all fully tested modules at $T = +17^{\circ}\text{C}$ (ATC)


Grade A
(9 modules)



Grade B
(1 modules)




Grade C
(1 modules)




Defective pixel $T = -10^{\circ}\text{C}$ (ATC)

Overlay of all fully tested modules at $T = -10^{\circ}\text{C}$ (ATC)


Grade A
(9 modules)



Grade B
(1 modules)




Grade C
(1 modules)




Defective pixel $T = -10^{\circ}\text{C}$ (BTC)

Overlay of all fully tested modules at $T = -10^{\circ}\text{C}$ (BTC)


Grade A
(10 modules)



Grade B
(0 modules)




Grade C
(1 modules)




Defective bump-bonds $T = 17^{\circ}\text{C}$ (ATC)

Overlay of all fully tested modules at $T = +17^{\circ}\text{C}$ (ATC)


Grade A
(9 modules)



Grade B
(1 modules)




Grade C
(1 modules)




Defective bump-bonds $T = -10^{\circ}\text{C}$ (ATC)

Overlay of all fully tested modules at $T = -10^{\circ}\text{C}$ (ATC)


Grade A
(9 modules)



Grade B
(1 modules)




Grade C
(1 modules)




Defective bump-bonds $T = -10^{\circ}\text{C}$ (BTC)

Overlay of all fully tested modules at $T = -10^{\circ}\text{C}$ (BTC)


Grade A
(10 modules)



Grade B
(0 modules)





Grade C
(1 modules)



Current at 150 V


Current at 150 V (in μA) at $T = 17^\circ\text{C}$ and $T = -10^\circ\text{C}$




Slope of IV-Curve

Slope of IV-Curve at $T = 17^{\circ}\text{C}$ and $T = -10^{\circ}\text{C}$

IVslope at $T = 17^{\circ}\text{C}$ (ATC)



IVslope at $T = -10^{\circ}\text{C}$ (ATC)




Current recalculation to $T = 17^{\circ}\text{C}$


Cross check of recalculated values with measured values

$T = 17^{\circ}\text{C}$ (ATC)
 $T = -10^{\circ}\text{C}$ (ATC)
 $T = -10^{\circ}\text{C}$ (BTC)

I150V




I150V ratio




$T = 17^{\circ}\text{C}$ (ATC)
 $T = -10^{\circ}\text{C}$ (ATC)
 $T = -10^{\circ}\text{C}$ (BTC)


IVslope



IVslope ratio




MeanNoise of chips




Noise in e^-

RelativeGainWidth of chips




PedestalSpread of chips



Pedestal Spread in e^-

Vcal Threshold Width



VcalThresholdWidth of chips



Vcal Thr. Width in e^-



Operational parameters I

Mean DACs I





Operational parameters II

Mean DACs II




Operational parameters III

Mean DACs III



Operational parameters at $T = +17^{\circ}\text{C}$ (ATC)

DAC distribution (of chips)




Operational parameters at $T = -10^{\circ}\text{C}$ (ATC)


DAC distribution (of chips)

DACs at $T = -10^{\circ}\text{C}$ (ATC)

Vana




VthrComp




Modules: M0432 ... M0487


CalDel




Ibias_DAC



Vtrim



VoffsetOp




Operational parameters at $T = +17^{\circ}\text{C}$ (BTC)


DAC distribution (of chips)

DACs at $T = -10^{\circ}\text{C}$ (BTC)

Vana




VthrComp




Modules: M0432 ... M0487


CalDel



Ibias_DAC



Vtrim



VoffsetOp

